




Structure and dynamics of ion-exchanged glasses

E.I. Kamitsos, R. Todorov and C.P. Varsamis

*Theoretical and Physical Chemistry Institute
National Hellenic Research Foundation, Athens, Greece*

**17th University Conference on Glass Science
&
1st International Materials Institute Workshop on
NEW FUNCTIONALITY IN GLASSES**




June 26-30, 2005 / State College, Pennsylvania

Outline of presentation

- Ion-exchange process: introduction & relevant literature
- Structure of ion-exchanged soda-lime-silica glass
- Structure of ion-exchanged $30\text{Na}_2\text{O}-70\text{B}_2\text{O}_3$ glass
- ac conductivity spectra of ion-exchanged $30\text{Na}_2\text{O}-70\text{B}_2\text{O}_3$ glass
- Summary

ION EXCHANGE PROCESS IN GLASS



ion “crowding”



compressive
stress



permanent
compression

$$T < T_g$$

M.E. Nordberg et. al.
J. Am. Ceram. Soc.
47 (1964) 215.




Applications:

- Chemical strengthening of commercial silicate glass
- Altering optical properties of glass (waveguides, micro-optics)


Open Questions:

- Is there a “mixed-alkali effect” in ion-exchanged glasses?
- How are K^+ ions accommodated within the glassy network?
- Can any changes in glass structure occur as a result of ion-exchange below T_g ?

Mixed Alkali Effect (MAE) in melt-grown glasses



Mixed alkali glasses by ion exchange



G. Tomandl & H.A. Schaeffer, Non-Cryst. Solids, Trans. Tech. Publ., pp. 480-485 (1977).

- ⇒ Ion-exchanged glasses below T_g do not show the MAE; i.e. resistivity shows a linear behavior throughout the ion-exchanged layer
- ⇒ Ion-exchange below T_g generates a different “mixed-alkali structure” than the melting process.

Mixed alkali glasses by ion exchange, cont.

C. Windisch & W.M. Risen, J. Non-Cryst. Solids, 44, 345 (1981).

(Na/Li) ion-exchanged $\text{Li}_2\text{O}-\text{Al}_2\text{O}_3-2\text{SiO}_2$ glasses / Raman spectroscopy

⇒ Network structure of ion-exchanged glasses is different from that of melt-grown glasses of the same stoichiometry

⇒ Annealing the ion-exchanged glass leads to network structure identical to that of the melt-grown glass.

S.N. Houde-Walter, J.M. Inman, A.J. Dent & G.N. Greaves, J. Phys. Chem. 97, 9330 (1993).

(Ag/Na) ion-exchanged $\text{Na}_2\text{O}-4\text{SiO}_2$ glasses / X-ray absorption fine structure (XAFS)

⇒ CN (Na/O) ≈ 5, r(Na-O)=2.30-2.32 Å

⇒ CN (Ag/O) ≈ 2, r(Ag-O)=2.08-2.23 Å (very similar to the environment of Ag in Ag_2O)

⇒ metal ions create their own characteristic environments in glass.

G. Berg & A. Ludwig, J. Non-Cryst. Solids, 170, 109 (1994).

(Ag/Na) ion-exchanged soda-lime silica glass / ac conductivity (at 10^2 , 10^3 Hz)

⇒ Concentration dependence of ac conductivity shows the typical mixed cation effect.

Mixed alkali glasses by ion exchange, cont.

T. Yano, K. Azegami, S. Shibata & M. Yamane, J. Non-Cryst. Solids, 222, 94 (1997).
(Ag/Na) ion-exchanged $\text{Na}_2\text{O}-2\text{SiO}_2$ glasses / X-ray photoelectron spectr. (XPS) & ^{29}Si -NMR
⇒ Ag ions induced a large charge redistribution on the glass network & an anomalous change in the distribution of Q^n silicate units
⇒ formation of Q^2 units at the expense of Q^3 units, but no Q^4 formation.

Y-K. Lee, Y.L. Peng & M. Tomozawa, J. Non-Cryst. Solids, 222, 125 (1997).
(K/Na) ion-exchanged soda-lime glass / FT-IR reflectance spectroscopy
⇒ Shift of the 1050 cm^{-1} peak is much larger than that caused by changes of the fictive temperature or composition. Thus, the shift of 1050 cm^{-1} peak is due mainly to the stress.
⇒ A new peak at 950 cm^{-1} develops with ion-exchange and is attributed to formation of non-bridging oxygen atoms.

M. Dubiel, B. Roling & M. Futing, J. Non-Cryst. Solids, 331, 11 (2003).
(K/Na) ion-exchanged soda-lime glass / ac conductivity spectroscopy (10^{-2} to 10^6 Hz)
⇒ No MAE for ion-exchange below T_g ; but presence of MAE for ion-exchange slightly above T_g
⇒ Spectral shape of ac conductivity indicates differences in the ion dynamics between glasses exchanged slightly above T_g and the corresponding melt-grown glasses.

EXPERIMENTAL DETAILS...

GLASS COMPOSITIONS & SPECTROSCOPIC TECHNIQUES

Glass Compositions Investigated (mol%)		
A. Soda-Lime-Silica Glasses		
Oxide	Pilkington float glass ($T_g=558\text{ }^{\circ}\text{C}$) (FGS0)	Soft glass tubing (T0)
SiO_2	71.78	71.62
Na_2O	12.44	14.02
CaO	8.76	6.19
K_2O	0.38	1.03
MgO	5.88	4.82
BaO	none	1.50
Al_2O_3	0.58	1.49
Fe_2O_3	0.04	0.02
SO_3	0.14	0.22

B. Sodium-Borate Glass: $30\text{Na}_2\text{O}-70\text{B}_2\text{O}_3$
($T_g=477\text{ }^{\circ}\text{C}$)

INFRARED SPECTRAL MEASUREMENTS:

- Specular reflectance at quasinormal incidence (11°)
⇒ use the same sample for continuous date acquisition in the mid- & far-IR range ($25\text{-}5,000\text{ cm}^{-1}$)


IMPEDANCE MEASUREMENTS:

- 5Hz -10MHz, f(T)






ELECTRON MICROPROBE ANALYSIS:

- K, Na profiles (Na K_{α} & K K_{α} X-rays produced by a 15 kV, 20-50 nA, e-beam)



ANALYSIS OF REFLECTIVITY SPECTRA




Kramers – Kronig transformation




Short-range order structure and metal ion-site vibrations in silicate glasses



Continuous Random Network (CRN) Model




Zachariasen, 1932



Warren-Biscoe, 1938

Q^n tetrahedral units in silicate glasses



Si





O (bridging)





O (non-bridging)

Short-range order structure and metal ion-site vibrations in silicate glasses







IR SPECTRA OF “SYNTHETIC” MIXED-CATION (Na^+/K^+) FLOAT GLASSES



“Synthetic” float glasses					
mol%	F1	F2	F3	F4	F5
Na_2O	12.44	9.61	6.41	3.21	0.38
K_2O	0.38	3.21	6.41	9.61	12.44



THERMALLY ION-EXCHANGED FLOAT GLASS: K⁺/Na⁺



ANNEALING OF ION-EXCHANGED (K^+/Na^+) FLOAT GLASS



FGS0: pristine float glass


FGS2: FGS0 thermally exchanged
in KNO_3 at 475 °C for 16h

FGS2A: FGS2 annealed in air
at 475 °C for 16 h





glass structure becomes
less homogeneous

Infrared spectra of single alkali borate glasses




IR SPECTRA OF “SYNTHETIC” MIXED-CATION BORATE GLASSES



$0.3[x\text{K}_2\text{O}-(1-x)\text{Na}_2\text{O}]-0.7\text{B}_2\text{O}_3$




THERMALLY ION-EXCHANGED $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ GLASS: K^+/Na^+
IR reflectance spectra




THERMALLY ION-EXCHANGED $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ GLASS: K^+/Na^+ IR absorption spectra






$\text{BO}_4^- \leftrightarrow \text{BO}_2\text{O}^-$
local structure rearranges
to meet the needs of K^+ ions

Conductivity spectra of the base glass: $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$




scaled conductivity spectra




see: B. Roling, A. Happe, K. Funke & M.D. Ingram,
Phys. Rev. Lett. 78 (1997) 2160.

Conductivity spectra of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ glass ion-exchanged in KNO_3




Comparison of conductivity spectra of the base glass $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ with those obtained after ion-exchange in KNO_3 at $450\text{ }^\circ\text{C}$ for 30 min




Scaled conductivity spectra of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ glass ion-exchanged in KNO_3 at $450\text{ }^\circ\text{C}$ for 30 min

scaled with σ_{dc} of the base glass




scaled with low-frequency σ_{dc} of the ion-exchanged glass



K^+/Na^+ ion exchange below T_g
leads to the development of a
highly resistive surface layer


Comparison of conductivity spectra of mixed alkali glasses

$0.3[x\text{K}_2\text{O}-(1-x)\text{Na}_2\text{O}]-0.7\text{B}_2\text{O}_3$: melt-grown vs ion-exchanged glasses




Comparison of activation energies for dc conductivity: melt-grown $0.3[x\text{K}_2\text{O}-(1-x)\text{Na}_2\text{O}]-0.7\text{B}_2\text{O}_3$ glasses vs ion-exchanged glasses

melt-grown



ion-exchanged



Dielectric spectra in the resistivity representation

Dielectric measurements: apply voltage $V(\omega) = V_m \sin(\omega t)$

measure current $I(\omega) = I_m \sin(\omega t + \delta)$

Complex impedance:

$$Z^*(\omega) = Z'(\omega) - iZ''(\omega)$$

$$Z' = |Z^*| \cos \delta, \quad Z'' = |Z^*| \sin \delta, \quad |Z^*| = \frac{V_m}{I_m}$$

Complex resistivity:

$$\rho^*(\omega) = \rho'(\omega) - i\rho''(\omega) = Z^*(\omega) \frac{S}{d}$$

d =sample thickness; S =electrode area


Complex conductivity:

$$\sigma^*(\omega) = \sigma'(\omega) + i\sigma''(\omega) = \frac{1}{\rho^*(\omega)}$$


$$\sigma'(\omega) = \frac{\rho'(\omega)}{[\rho'(\omega)]^2 + [\rho''(\omega)]^2}$$

$$\rho'(\omega) = \frac{\sigma'(\omega)}{[\sigma'(\omega)]^2 + [\sigma''(\omega)]^2}$$


Resistivity spectra of the base glass: $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$




scaled resistivity spectra




Resistivity spectra of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ glass ion-exchanged in KNO_3





Resistivity spectra of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ glass ion-exchanged in KNO_3



“Annealing” of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ ion-exchanged glass



"Annealing" of the $0.3\text{Na}_2\text{O}-0.7\text{B}_2\text{O}_3$ ion-exchanged glass, cont.



SUMMARY

- Structural aspects of ion-exchanged glasses: soda-lime-silica & sodium-borate

⇒ Alkali ion motion in the glass matrix below T_g , caused either by ion exchange and/or annealing, is accompanied by local structural rearrangements/relaxations involving short-range order structural units (Cation Induced Relaxations Of the Network, CIRON).

⇒ The structural rearrangements depend on the nature of the glass network and the type of the foreign cation introduced into the glass structure:

Soda-lime-silica glass:



Sodium-borate glass:



⇒ The structure of an ion-exchanged glass resembles that of the corresponding melt-grown mixed alkali glass (i.e. similar SRO structure and nature of sites hosting metal ions).

SUMMARY cont.

- Ac conductivity aspects of ion-exchanged glasses: sodium-borate glass

⇒ The resistivity of the ion-exchanged (surface) layer can be described in terms of the resistivities of melt-grown K/Na mixed alkali glasses.

ACKNOWLEDGMENT

Univ. of Aberdeen, Scotland: M.D. Ingram, J. Davidson, M.H. Wu, A. Coats
NHRF, Athens: J. Kapoutsis, P. Machowski.

- ⇒ Royal Society / NHRF (exchange program)
- ⇒ General Secretariat for Research and Technology / Ministry of Development in Greece
- ⇒ European Union (project HPMD-CT-2000-00033).